EXPANDABLE BRAIDED SLEEVING



Monoflex[®] HT PRODUCT HIGHLIGHTS



Maximum Operating Temperature: 150°C

Exhibits Low Outgassing



RoHS/REACH Compliant



Flame Resistant



UL Temperature & VW-1 Rated (File #E118600) **Atkins & Pearce's Monoflex**[®] **HT** is an unique expandable sleeving offering made of ethylene chlorotrifluoroethylene (ECTFE) ideal for applications where flammability, impact strength endurance, and low outgassing are primary concerns. This self-extinguishing and flame resistant sleeving exhibits low outgassing and has high impact strength. It's low flame spread and low smoke generation properties make it an ideal sleeving for plenum applications.

Monoflex[®] HT is available in a couple of colors to assist in special identification for safety and other needs. Below is a complete list of the standard sizes we offer in this sleeving. Additionally, cut lengths are available upon request.

NOMINAL ID	MAX EXPANSION	WALL THICKNESS
1/8 inch	1/4 inch	0.028 inch
1/4 inch	7/16 inch	0.028 inch
3/8 inch	5/8 inch	0.028 inch
1/2 inch	3/4 inch	0.028 inch
3/4 inch	1-1/4 inch	0.028 inch
1 inch	1-5/8 inch	0.028 inch
1-1/4 inch	1-3/4 inch	0.028 inch
1-1/2 inch	2 inch	0.028 inch
1-3/4 inch	2-3/4 inch	0.028 inch

For additional information on Monoflex® HT's features and color offerings please contact our Sales & Marketing Team via phone or email at the addresses below.



EXPANDABLE BRAIDED SLEEVING

Performance Metrics

PROPERTY (TEST)	RESULT		
Abrasion (ASTM D-4060)	7,500 cycles		
Hardness, Shore D (ASTM D-2240)	75		
Low Temperature Flexibility (below freezing)	No cracking or deformation		
Limiting Oxygen Index (ASTM D-2863)	52%		

Thermals

MAX OPERATING TEMPERATURE	MELTING POINT
150°C / 302°F	242°C / 467°F

Chemical Resistance	Poor	Fair	Good	Excellent	Monofilament Properties
					SINGLE-STRAND DIAMETER
Degradation by Alcohols					0.011 inch
Degradation by Alkali					DENSITY
Degradation by Hydrocarbons					1.68 g/cc
Degradation by Katonee					SINGLE-STRAND TENSILE STRENGTH
Degradation by Ketones					2.7 lbs. (minimum)
Degradation by Organic Acids					MOISTURE ABSORPTION
Degradation by Strong Acids					< 0.10%
Descredation by UV Links					OUTGASSING
Degradation by UV Light					Low Outgassing
K	K			s and t	CONTACT US!

Our manufacturing facility and office is centrally located in northern Kentucky.

Atkins&Pearce

One Braid Way, Covington, KY 41017 USA 1.800.837.7477 | info@atkinsandpearce.com | www.atkinsandpearce.com

LAST REVISED: April 2023 | The suggested application is provided by Atkins & Pearce merely as an additional tool to assist in making an appropriate selection. This is only provided to serve as suggestions of sleeving that may be appropriate based on certain criteria and should not be relied upon as determinative or as a substitute for customer testing. Many variables exist in a sleeve's flexibilities, resistances, and treatment. Final product selection should always be confirmed through the customer's own testing process to determine if a specific product is the correct choice for a particular application. Atkins & Pearce is not responsible for selections made by the customer using any of the reference material provided. For optimal performance in specific systems, we strongly recommend that customers conduct exhaustive tests in their own lab and consider retaining samples for their future internal reference. The importance of product testing and data validation cannot be overstated. As the customer, you and your company are responsible for appropriate lytesting all Atkins & Pearce product used in your application and for making the final selection based upon meeting appropriate safety and electrical standards. Atkins & Pearce makes no representation or warranty, expressed or implied, at law or in equity, in respect of the information provided, including, without limitation, with respect to merchantability or fitness for any particular purpose, which representations or warranties are hereby expressly disclaimed.